

REMOVABLE DOUBLE COATED POLYESTER TAPE

A 1 mil (25 micron) polyester film differentially coated with two separate acrylic adhesives. Exposed side is a controlled tack adhesive system to allow end user easy removal with no residue. Liner side is an aggressive, high tack, high peel, and high shear formulation. Both adhesives are excellent in low temperatures as well as normal and are resistant to UV, moisture, solvents, mild acids, oil, and grease. Excellent adhesion to metals, glass, films, paper, and some treated polyolefin's.

Name	Imperial Typical Value	Typical Value (Metric)
Thickness Adhesive Exposed	2.8 mils	0.071 mm
Thickness Liner	3.75 mils	0.093 mm
Peel Adhesion Exposed	53 oz/inch width	15.0 N/2.5 cm
Shear Strength Exposed	96+ hrs @ 2.2 psi	96+ hrs @ 15.2 kPa
Tensile Strength	16 lbs/inch width	72.5 N/2.5 cm
Elongation	100%	100%
Minimum Appl	35 degrees F	2 degrees C
Maximum Use Temp	275 degrees F	135 degrees C
Standard Widths	1/4" to 54	" 6.5 mm to 1371 mm
Standard Length	60 yds	250 yds

Typical values are not intended to be used for specification development. Technical data is believed to be true and accurate; Venture Tape recommends that the purchaser test for fitness of use in all applications.

Contact Venture Tape today for a complete list of products or a free sample
 Toll Free North America 800-343-1076
 From United Kingdom 0-800-962-957
 From Australia 1-800-122-797
www.venturetape.com
www.boma.it



USA
 Venture Tape Corp.
 30 Commerce Road
 Rockland, MA 02370
 781-331-5900
 FAX 781-871-0065
www.venturetape.com

Europe - Venture Tape
 Venture Tape Europe Corp.
 Units 5 - 6, Faraday Close,
 Drayton Fields, Daventry,
 Northamptonshire, England NN11 8RD
 (0) 1327 876555
 FAX (0) 1327 876444

Australasia
 Venture Tape Australasia, Pty., Ltd.
 11B Production Drive
 Campbellfield, VIC 3061
 Australia
 (03) 9357 6025
 FAX (03) 9357 6045