

2 MIL UNSUPPORTED TRANSFER FILM

A 2 mil (50 micron) unsupported acrylic transfer film.

| Name | Imperial Typical Value | Typical Value (Metric) |
|------------------------|------------------------|------------------------|
| Thickness Liner | 2.0 mils | 0.0506 mm |
| Peel Adhesion Exposed | 70.0 oz/inch width | 20.0 N/2.5 cm |
| Shear Strength Exposed | 48 hrs @ 2.2 psi | 48 hrs @ 15.2 kPa |
| Minimum Appl | 32 degrees F | 0 degrees C |
| Maximum Use Temp | 300 degrees F | 152 degrees C |

Typical values are not intended to be used for specification development. Technical data is believed to be true and accurate; Venture Tape recommends that the purchaser test for fitness of use in all applications.

Contact Venture Tape today for a complete list of products or a free sample
Toll Free North America 800-343-1076
From United Kingdom 0-800-962-957
From Australia 1-800-122-797
www.venturetape.com
www.boma.it



USA
Venture Tape Corp.
30 Commerce Road
Rockland, MA 02370
781-331-5900
FAX 781-871-0065
www.venturetape.com

Europe - Venture Tape
Venture Tape Europe Corp.
Units 5 - 6, Faraday Close,
Drayton Fields, Daventry,
Northamptonshire, England NN11 8RD
(0) 1327 876555
FAX (0) 1327 876444

Australasia
Venture Tape Australasia, Pty., Ltd.
11B Production Drive
Campbellfield, VIC 3061
Australia
(03) 9357 6025
FAX (03) 9357 6045