

PROPOSED CONSTRUCTION

A thin, strong and conformable polyethylene film tape coated with an ultra aggressive high performance acrylic copolymer pressure sensitive adhesive. For use in a broad range of applications at both low and moderately high temps. This product had very high tack (quick stick) and good adhesion properties.

Name	Imperial Typical Value	Typical Value (Metric)
Thickness Carrier	4.75 mils	0.1206 mm
Thickness Adhesive Exposed	2.0 mils	0.0508 mm
Peel Adhesion Exposed	70 oz/inch width	19.8 N/2.5 cm
Shear Strength Exposed	>8 hrs @ 2.2 psi	>8 hrs @ 15.2 kPa
Tensile Strength	13.0 lbs/inch width	56.5 N/2.5 cm
Elongation	250%	250%
Minimum Appl	10 degrees F	-12 degrees C
Maximum Use Temp	175 degrees F	80 degrees C

Typical values are not intended to be used for specification development. Technical data is believed to be true and accurate; Venture Tape recommends that the purchaser test for fitness of use in all applications.

Contact Venture Tape today for a complete list of products or a free sample
 Toll Free North America 800-343-1076
 From United Kingdom 0-800-962-957
 From Australia 1-800-122-797
www.venturetape.com
www.boma.it



USA
 Venture Tape Corp.
 30 Commerce Road
 Rockland, MA 02370
 781-331-5900
 FAX 781-871-0065
www.venturetape.com

Europe - Venture Tape
 Venture Tape Europe Corp.
 Units 5 - 6, Faraday Close,
 Drayton Fields, Daventry,
 Northamptonshire, England NN11 8RD
 (0) 1327 876555
 FAX (0) 1327 876444

Australasia
 Venture Tape Australasia, Pty., Ltd.
 11B Production Drive
 Campbellfield, VIC 3061
 Australia
 (03) 9357 6025
 FAX (03) 9357 6045