

# 460 Series

## VINYL SEAMING TAPE

Venture Tape 460 is a 3.2 mil embossed vinyl coated with an aggressive acrylic pressure sensitive adhesive. Specifically designed for use as a seaming tape for vinyl faced fiberglass insulation, Venture Tape 460 applies easily and excels in demanding temperature and humidity applications, providing superior performance and durability over a wide range of conditions.

**Primary Use:** Seaming vinyl faced fiberglass insulation in metal buildings and for water heater blanket insulation.

### Features & Benefits

- Specifically designed for seaming vinyl faced

Name	Imperial Typical Value	Typical Value (Metric)
Thickness Carrier	3.2 mils	205.7 $\hat{I}$ ¼m
Thickness Adhesive Exposed	1.8 mils	45.7 $\hat{I}$ ¼m
Thickness Liner	3.1 mils	78.7 $\hat{I}$ ¼m
Peel Adhesion Exposed	57 oz/inch width	15.8 N/25 mm
Shear Strength Exposed	>4 hrs	>4 hrs
Tensile Strength	1980 lbs/inch width	8807 N/25 mm
Elongation	350%	350%
Minimum Appl	35 degrees F	-37 degrees C
Maximum Use Temp	260 degrees F	127 degrees C

Typical values are not intended to be used for specification development. Technical data is believed to be true and accurate; Venture Tape recommends that the purchaser test for fitness of use in all applications.

**Contact Venture Tape today for a complete list of products or a free sample**  
Toll Free North America 800-343-1076  
From United Kingdom 0-800-962-957  
From Australia 1-800-122-797  
[www.venturetape.com](http://www.venturetape.com)  
[www.boma.it](http://www.boma.it)



**USA**  
Venture Tape Corp.  
30 Commerce Road  
Rockland, MA 02370  
781-331-5900  
FAX 781-871-0065  
[www.venturetape.com](http://www.venturetape.com)

**Europe - Venture Tape**  
Venture Tape Europe Corp.  
Units 5 - 6, Faraday Close,  
Drayton Fields, Daventry,  
Northamptonshire, England NN11 8RD  
(0) 1327 876555  
FAX (0) 1327 876444

**Australasia**  
Venture Tape Australasia, Pty., Ltd.  
11B Production Drive  
Campbellfield, VIC 3061  
Australia  
(03) 9357 6025  
FAX (03) 9357 6045